



PARK  
ELECTROCHEMICAL  
CORP.

## Selector Guide

This Selector Guide is a quick index of our standard resins and reinforcements. Product data sheets that provide detailed information about specific prepreg systems are available on the web at [www.parkelectro.com](http://www.parkelectro.com)



### **Nelcote® Advanced Composite Prepregs for Critical Applications**

**Aircraft primary and secondary structures, interiors and radomes**

**Ablative materials for rocket nozzles, motors and heat shields and thermal insulation**

**RF and microwave materials for radomes, reflectors and signature control structures.**

[www.parkelectro.com](http://www.parkelectro.com)



# Nelcote® Advanced Composite Materials

## Application: Aircraft Primary and Secondary Structures

Materials Features and Applications	Reinforcements ----- Product Forms	Cure Temp °C / °F	Dry Tg* °C / °F	Autoclave Cure	Vacuum Cure	Press Molding
<b>E-761 250°F (125°C) Cure Epoxy Prepreg</b> Self adhesive prepreg for sandwich applications. Flame retardant (per FAR25.853) with good RF properties. Wide process latitude. Wet service temperature up to 160°F <i>Applications: Aircraft and mass-transit interiors, Aircraft structures, Radomes</i>	Fiberglass, Carbon, Aramid (including Kevlar®), Spectra®, Quartz (including Astroquartz) ----- Fabric	120 / 250	122 / 252	X	X	X
<b>E-765 250°F (125°C) Cure Epoxy Prepreg</b> Toughened epoxy for aerospace structures. Wide processing window. Wet service temperature up to 180°F. FAA accepted AGATE design allowables database available <i>Applications: Aircraft primary and secondary structures, Radomes</i>	Fiberglass, Carbon, Spectra®, Quartz (including Astroquartz) ----- Fabric, Uni-tape	125-135 260-280	195 / 381	X	X	X

<b>E-746 350°F (180°C) Cure Epoxy Prepreg</b> Modified epoxy resin system. Excellent mechanical properties after long-term high temperature exposure. Good RF properties. Meets requirement of Mil-R-9300B Type II. Service temperatures up to 500°F after post-cure <i>Applications: Aircraft structures, Radomes, Nacelles, Inlet ducts, Fairings</i>	Fiberglass, Quartz (including Astroquartz) ----- Fabric	180 / 350	205 / 401	X		
<b>E-752 350°F (180°C) Cure Epoxy Prepreg</b> Tough, 350°F cure system designed for aerospace primary structures. High service temperature and moisture resistance. Wet service temperature up to 250°F. FAA approved NCAMP design allowables database in process. <i>Applications: Aircraft structures</i>	Fiberglass, Carbon ----- Fabric, Uni-tape	180 / 350	210 / 410	X	X	X

## Application: Aircraft and Mass Transit Interiors

<b>F-529 Halogen-Free Phenolic Prepreg</b> Halogen-free prepreg for interior applications. Excellent FST and heat-release properties. White appearance after cure. Self-adhesive for sandwich structures <i>Applications: Aircraft and mass-transit interiors</i>	Fiberglass, Carbon ----- Fabric	120-150 250-300	120 / 248	X	X	X
<b>E-761 250°F (125°C) Cure Epoxy Prepreg</b> Self adhesive prepreg for sandwich applications. Flame retardant (per FAR25.853) with good RF properties. Wide process latitude. Wet service temperature up to 160°F <i>Applications: Aircraft and mass-transit interiors, Aircraft structures, Radomes</i>	Fiberglass, Carbon, Aramid (including Kevlar®), Spectra®, Quartz (including Astroquartz) ----- Fabric	120 / 250	122 / 252	X	X	X
<b>E-766B 250°F (125°C) Cure Epoxy Prepreg</b> Toughened, low tack epoxy. Self-adhesive prepreg for sandwich applications. Flame retardant. Controlled flow properties. Service temperature up to 160°F <i>Applications: Sandwich panels, Radomes</i>	Fiberglass, Carbon, Aramid (including Kevlar®) ----- Fabric	125-135 260-280	93 / 200	X	X	X

## Application: High Temperature and Specialty

<b>V-303 Non-MDA Polyimide Prepreg</b> Non-MDA condensation polyimide resin system. Very high service temperature <i>Applications: Aircraft structures, Radomes</i>	Fiberglass, Quartz (including Astroquartz), Carbon ----- Fabric	180 / 350 plus 550 FPC	315 / 600	X		X
<b>V-341 Polybutadiene Prepreg</b> Very low loss prepreg for critical RF applications. Self adhesive for foam core sandwich panels. Excellent chemical and fungus resistance <i>Applications: High performance radomes, Reflectors, Antennas</i>	Fiberglass, Quartz (including Astroquartz) ----- Fabric	180 / 350	93 / 200	X		X
<b>V-376 Cyanate Ester</b> Excellent RF properties (low loss). Low moisture absorption. Self adhesive prepreg for sandwich applications. Ideal alternative to BMI and polyimide systems <i>Applications: High performance radomes, Reflectors, Antennas</i>	Fiberglass, Quartz (including Astroquartz) ----- Fabric	180 / 350	204 / 400	X		X
<b>S-860 Silicone Prepreg</b> Silicone resin system with excellent high temperature properties <i>Applications: High performance radomes</i>	Fiberglass ----- Fabric	180 / 350	260 / 500	X		X

\* DMA peak tan δ

# Nelcote® Advanced Composite Materials

## Application: Phenolic Ablative

Features	Reinforcements ----- Product Forms	Cure Temp °C / °F	Dry Tg* °C / °F	Autoclave Cure	Vacuum Cure	Press Molding
<b>F-502 Phenolic Ablative Prepreg</b> Combines high-strength and ablative properties for demanding applications. Low thermal expansion <i>Applications: Ablative rocket nozzles, Ducting, Secondary structures</i>	Fiberglass, Carbon, Quartz (including Astroquartz) ----- Fabric, CMC / Biased Tape	120-180 250-350	260 / 500	X		X
<b>F-554 Phenolic / Silica Ablative Prepreg</b> High purity silica filled resin system coated on commercial or aerospace grade silica fabric. Combines higher strength and ablative properties for demanding applications. Low thermal expansion <i>Applications: Ablative rocket nozzles, Combustion chambers, Heat shields, Rocket motor throat sections, Exhaust gas management</i>	Silica ----- Fabric, CMC / Biased Tape	120-180 250-350	260 / 500	X		X
<b>F-555 Phenolic / Carbon Ablative Prepreg</b> Carbon-loaded resin system. Combines high-strength and ablative properties for demanding applications. Low thermal expansion. Also available in a low density version <i>Applications: Ablative rocket nozzles, Combustion chambers, Heat shields, Rocket motor throat sections</i>	Carbonized Rayon (including C2 and NARC) ----- Fabric, CMC / Biased Tape	120-180 250-350	260 / 500	X		X
<b>F-557 Phenolic / Silica Ablative Prepreg</b> High purity Silica filled resin system coated on commercial or aerospace grade silica fabric. Combines higher strength and ablative properties for demanding applications. Low thermal expansion <i>Applications: Ablative rocket nozzles, Combustion chambers, Heat shields, Rocket motor throat sections, Exhaust gas management</i>	Silica ----- Fabric, CMC / Biased Tape	120-180 250-350	260 / 500	X		X
<b>F-562 Modified Phenolic Ablative Prepreg</b> Elastomer modified resin system coated on silica or carbonized rayon <i>Applications: Ablative rocket nozzles, Combustion chambers, Heat shields, Rocket motor throat sections, Exhaust gas management</i>	Carbonized Rayon (including C2 and NARC), Silica ----- Fabric	120-180 250-350	260 / 500	X		X

## Application: Polyester Prepreg

<b>P-600 Polyester Prepreg</b> General purpose polyester resin system. Non-styrenated / Low VOC. Good alternative to wet-layup processing <i>Applications: Aircraft structures, Industrial parts</i>	Fiberglass ----- Fabric	80-120 180-250	71 / 160	X	X	X
<b>P-601 Polyester Prepreg</b> Polyester resin system designed for Woven roving applications. Non-styrenated / Low VOC. Good alternative to wet-layup processing <i>Applications: Radomes</i>	Fiberglass ( 18 oz woven roving), Polyester ----- Fabric	80-120 180-250	71 / 160	X	X	X
<b>P-650M Polyester Prepreg</b> Modified diallyphthallate resin system. Excellent wet electrical properties. Non-styrenated / Low VOC <i>Applications: Aircraft structures, Radomes, Antenna, Embossing die fabrication</i>	Fiberglass ----- Fabric	120-150 250-300	120 / 250	X	X	X
<b>P-650R Polyester Prepreg</b> Designed for optical clarity. Good mechanical and electrical properties. Non-styrenated / Low VOC <i>Applications: Optical clarity requirements, Aircraft lighting, etc.</i>	Fiberglass ----- Fabric	120-150 250-300	120 / 250	X	X	X
<b>P-670F Polyester Prepreg</b> High temperature service. Flame retardant. Excellent electrical and mechanical properties. Non-styrenated / Low VOC <i>Applications: Aircraft structures, Radomes, Tooling</i>	Fiberglass ----- Fabric	120-150 250-300	120 / 250	X	X	X
<b>P-670I Polyester Prepreg</b> High temperature service. Flame retardant. Excellent electrical and mechanical properties. Non-styrenated / Low VOC Antimony free <i>Applications: Aircraft structures, Radomes, Tooling</i>	Fiberglass ----- Fabric	120-150 250-300	120 / 250	X	X	X

## Nelcote® RF / Microwave Prepreg Systems

### Electromagnetic and Thermal Properties

Resin/Reinforcement	Cure Temp. °F (°C)	Dielectric Constant X-Band*	Loss Tangent X-Band*	Service Temp. °F (°C)
V-341 Polybutadiene / Quartz	350 (180)	3.1	0.001	200 (93)
V-376 Cyanate Ester / Quartz	350 (180)	3.2	0.005	400 (204)
V-376 Cyanate Ester / Fiberglass	350 (180)	4.0	0.011	400 (204)
E-761 Epoxy / Quartz	250 (120)	3.4	0.009	200 (93)
E-761 Epoxy / Spectra®	230 (110)	2.7	0.004	180 (82)
E-761 Epoxy / Fiberglass	250 (120)	4.2	0.013	200 (93)
E-746 Hi-Temp. Epoxy / Quartz	350 (180)	3.6	0.012	500 (260)
E-746 Hi-Temp. Epoxy / Fiberglass	350 (180)	4.2	0.016	500 (260)
E-765 Epoxy / Quartz	250 (120)	3.4	0.015	275 (135)
E-765 Epoxy / Fiberglass	250 (120)	4.5	0.020	275 (135)
P-670I Polyester / Fiberglass	250 (120)	4.0	0.014	250 (120)
P-615 SuperVue / Spectra	230 (110)	2.4	0.004	160 (71)
S-860 Silicone / Fiberglass	350 (180)	4.2	0.013	500 (260)

\* Nominal electrical values, subject to fiber volume and test technique.

## Nelcote® FAA Accepted Design Allowable Databases

Resin	Reinforcement	FAW (gsm)	CPT in. (mm)	FAA Database
E-765	3K Plain Weave T300 Carbon	193	0.009 (0.23)	AGATE
	6K Five Harness T300 Carbon	370	0.016 (0.41)	AGATE
	T700 Unidirectional Carbon	150	0.005 (0.13)	AGATE
	7781 Fiberglass	300	0.009 (0.23)	AGATE
E-752	3K Plain Weave G30-500 Carbon	193	0.009 (0.23)	NCAMP*
	AS7 Unidirectional Carbon	145	0.005 (0.13)	NCAMP*

\* Full data release expected Q1 2010

## Manufacturing Aids

**PeelCote®** Resin coated for use as first ply against mold surface, Reduces finish labor  
*Applications:* Improve laminate surface, Prep for bonding/paint

**CoreFix®** Disposable prepreg used to stabilize honeycomb materials during handling and machining. Several advantages versus traditional prepreps and double-backed tapes  
*Applications:* Precision honeycomb machining aid

## Important Notice:

Park Electrochemical Corp. reserves the right to make changes without notice to any products described herein. Park does not assume any liability arising out of the application or use of any product described herein; and it does not grant any license under its patent or other rights or any such rights of others. Park also disclaims all warranties whether expressed, implied or statutory, including implied warranties of merchantability or fitness for a particular purpose.

Given the variety of factors that can affect the use and performance of Park's Nelcote products, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the product to determine whether it is fit for a particular purpose and/or suitable for the user's method of application. These factors may include, but are not limited to, the materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform.

## Nelcote® Advanced Composite Materials

North America  
Connecticut +1.203.755.1344  
Kansas +1.316.283.6500  
Asia Pacific +656.861.7117  
Europe +33.562.985.290

[www.parkelectro.com](http://www.parkelectro.com) / [nelcotecs@parkelectro.com](mailto:nelcotecs@parkelectro.com)

